

Norsok M-501 Compliant Coating Systems



Norsok System Number 3B (M-501 Rev 4)

Ballast water tanks / internal seawater filled compartments

<u>Surface Treatment</u>	<u>Specification</u>	<u>DFT (µm)</u>	<u>Sales Codes</u>	<u>Product Comments</u>	<u>Corrosion Creep Value</u>	<u>Test Report Number</u>
Sa2½ Shop primer Interplate 997 @ 15µm dft	Intergard 423 Intergard 423	150 150	KBA420 / 423 KBA420 / 423		< 3mm	NITN 44230 KA04
Sa2½ Shop primer Interplate 997 @ 15µm dft	Intershield 300 Intershield 300	175 175	ENA300 / 303 ENA301 / 303	Tested in accordance with Rev 3 for System 7. Test results are in accordance with Rev 4 system 3B	< 3mm	Marintek 78.1167.07