

System 1

Telefon: 55 95 80 00

Telefax: 55 95 80 50

Web: www.hempel.com

Coating System	Surface Treatment	Specification	DFT μ	Product Comments	Corrosion Creep Value	Chalking	Test Report Number
1 - 1	Shopprimed steel	HEMPADUR ZINC 17360 HEMPADUR MASTIC 45880 HEMPATHANE TOPCOAT 55910	50 210 <u>75</u> 335		NORSOK Requirement < 3 mm	0	TI 36028 KA03
1 - 2	Shopprimed steel	HEMPADUR ZINC 17360 HEMPADUR MASTIC 45880 HEMPEL'S ENAMEL 55850	50 210 <u>75</u> 335		NORSOK Requirement < 3 mm	0	TI 36028 KA02
1 - 3	Sa 2,5	HEMPEL'S GALVOSIL 15700 HEMPADUR 45230 HEMPADUR 45143 HEMPATHANE TOPCOAT 55210	70 100 125 <u>50</u> 345		STATOIL Requirement < 1 mm	0	TI 39882 KA09
1 - 4	Shopprimed steel	HEMPADUR ZINC 17360 HEMPADUR 15560 HEMPADUR 15560 HEMPATHANE TOPCOAT 55210	40 125 125 <u>50</u> 340		NORSOK Requirement < 3 mm	0	TI 39882 KA08
1 - 5	Sa 2,5	HEMUDUR ZINC 18560 HEMUDUR 18504 HEMUCRYL ENAMEL 58040	70 110 <u>60</u> 240	Water-borne coating system.	STATOIL Requirement < 1 mm	0	TI 50327 MK01